

GEOTEX® 601

GEOTEX 601 is a polypropylene, staple fiber, needlepunched nonwoven geotextile manufactured at one of SI Geosolutions' facilities that has achieved ISO-9002 certification for its systematic approach to quality. The fibers are needed to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils. **GEOTEX 601** conforms to the property values listed below¹ which have been derived from quality control testing performed by one of SI Geosolutions' GAI-LAP accredited laboratories:

MARV²

PROPERTY	TEST METHOD	ENGLISH	METRIC
Mechanical			
Grab Tensile Strength	ASTM D4632	160 lbs	710 N
Grab Elongation	ASTM D4632	50%	50%
Puncture Strength	ASTM D4833	85 lbs	375 N
Mullen Burst	ASTM D3786	280 psi	1930 kPa
Trapezoidal Tear	ASTM D4533	60 lbs	265 N
Wide Width Tensile	ASTM D4595	60 lb-in	10.5 Kn/m
Endurance			
UV Resistance	ASTM D4355	70%	70%
Hydraulic			
Apparent Opening Size (AOS)	ASTM D4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D4491	1.30 sec ⁻¹	1.30 sec ⁻¹
Permeability	ASTM D4491	0.24 cm/sec	0.24 cm/sec
Water Flow Rate	ASTM D4491	110 gpm/ft ²	4480 l/min/m ²
Roll Sizes			
		150 in x 100 yds	3.81 m x 91.5 m
		180 in x 100 yds	4.57 m x 91.5 m

NOTES:

¹ The property values listed below are effective 9/6/00 are subject to change without notice.

² Values shown are in weaker principal direction. Minimum average roll values are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT FURNISHED HEREUNDER OTHER THAN AT THE TIME OF DELIVERY IT SHALL BE OF THE QUALITY AND SPECIFICATION STATED HEREIN. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED, AND, TO THE EXTENT THAT IT IS CONTRARY TO THE FOREGOING SENTENCE, ANY IMPLIED WARRANTY OF MERCHANTABILITY IS EXPRESSLY EXCLUDED. ANY RECOMMENDATIONS MADE BY SELLER CONCERNING THE USES OR APPLICATIONS OF SAID PRODUCT ARE BELIEVED RELIABLE AND SELLER MAKES NO WARRANTY OF RESULTS TO BE OBTAINED. IF THE PRODUCT DOES NOT MEET SYNTHETIC INDUSTRIES CURRENT PUBLISHED SPECIFICATIONS, AND THE CUSTOMER GIVES NOTICE TO SYNTHETIC INDUSTRIES BEFORE INSTALLING THE PRODUCT, THEN SYNTHETIC INDUSTRIES WILL REPLACE THE PRODUCT WITHOUT CHARGE OR REFUND THE PURCHASE PRICE.